

GUNPAD

Tested: 26/03/2008 6:54

Number of Samples= 51

CLIENT: GUNALLO

Ref: YOUNG RAMS

TAG	GREASY WT (KG)	GWT %	MICRON u	MIC DEV	C.V.	S.D.	%>30u	CURVATURE (deg/mm)	SPINNING FINENESS
<b>Flock</b>									
<b>Avg &gt;</b>			<b>18.4</b>		<b>16.0</b>	<b>2.9</b>	<b>0.5</b>	<b>98</b>	<b>17.2</b>
<b>036</b>			<b>17.5</b>	<b>-0.8</b>	<b>15.4</b>	<b>2.7</b>	<b>0.0</b>	<b>98</b>	<b>16.4</b>
046			17.0	-1.4	12.9	2.3	0.0	101	15.6
<b>076</b>			<b>18.2</b>	<b>-0.1</b>	<b>16.5</b>	<b>3.0</b>	<b>0.2</b>	<b>92</b>	<b>17.1</b>
077			19.3	0.9	16.1	3.1	0.6	86	18.0
<b>129</b>			<b>18.3</b>	<b>0.0</b>	<b>15.3</b>	<b>2.8</b>	<b>0.8</b>	<b>101</b>	<b>17.1</b>
230			19.4	1.0	18.6	3.6	1.0	102	18.5
<b>246</b>			<b>19.3</b>	<b>0.9</b>	<b>15.5</b>	<b>3.0</b>	<b>0.6</b>	<b>89</b>	<b>18.0</b>
249			18.0	-0.4	14.4	2.6	0.2	95	16.6
<b>251</b>			<b>17.3</b>	<b>-1.1</b>	<b>16.2</b>	<b>2.8</b>	<b>0.2</b>	<b>96</b>	<b>16.2</b>
274			19.8	1.5	15.2	3.0	0.8	89	18.5
<b>329</b>			<b>16.4</b>	<b>-1.9</b>	<b>14.6</b>	<b>2.5</b>	<b>0.0</b>	<b>85</b>	<b>15.2</b>
331			16.1	-2.2	17.4	2.8	0.0	102	15.3
<b>431</b>			<b>18.5</b>	<b>0.1</b>	<b>17.3</b>	<b>3.2</b>	<b>0.6</b>	<b>95</b>	<b>17.5</b>
439			19.0	0.7	15.3	2.9	1.0	98	17.7
<b>512</b>			<b>17.3</b>	<b>-1.0</b>	<b>14.5</b>	<b>2.5</b>	<b>0.2</b>	<b>102</b>	<b>16.1</b>
594			19.2	0.8	15.6	3.0	0.4	99	17.9
<b>610</b>			<b>18.9</b>	<b>0.5</b>	<b>17.5</b>	<b>3.3</b>	<b>0.6</b>	<b>89</b>	<b>17.9</b>
664			17.8	-0.5	15.2	2.7	0.6	96	16.6
<b>676</b>			<b>19.4</b>	<b>1.0</b>	<b>16.5</b>	<b>3.2</b>	<b>0.6</b>	<b>97</b>	<b>18.2</b>
840			18.4	0.1	14.7	2.7	0.2	76	17.1
<b>GP 001</b>			<b>22.3</b>	<b>4.0</b>	<b>17.0</b>	<b>3.8</b>	<b>2.0</b>	<b>104</b>	<b>21.0</b>
P 022			18.1	-0.3	16.6	3.0	0.2	104	17.0
<b>P 024</b>			<b>18.8</b>	<b>0.5</b>	<b>14.9</b>	<b>2.8</b>	<b>0.2</b>	<b>93</b>	<b>17.5</b>
P 252			19.3	1.0	13.5	2.6	0.2	94	17.8
<b>P 282</b>			<b>18.2</b>	<b>-0.1</b>	<b>20.9</b>	<b>3.8</b>	<b>0.8</b>	<b>101</b>	<b>17.7</b>
P 283			18.7	0.3	18.2	3.4	0.8	87	17.8
<b>P 412</b>			<b>18.0</b>	<b>-0.4</b>	<b>15.1</b>	<b>2.7</b>	<b>0.0</b>	<b>102</b>	<b>16.7</b>
P 418			16.3	-2.1	17.2	2.8	0.2	109	15.4
<b>P 421</b>			<b>17.7</b>	<b>-0.7</b>	<b>15.8</b>	<b>2.8</b>	<b>0.4</b>	<b>101</b>	<b>16.5</b>
P 430			17.7	-0.7	14.1	2.5	0.4	110	16.4
<b>P 443</b>			<b>18.2</b>	<b>-0.1</b>	<b>18.7</b>	<b>3.4</b>	<b>0.4</b>	<b>98</b>	<b>17.4</b>
P 504			18.1	-0.2	17.1	3.1	0.4	91	17.1
<b>P 525</b>			<b>17.5</b>	<b>-0.9</b>	<b>16.0</b>	<b>2.8</b>	<b>0.8</b>	<b>90</b>	<b>16.4</b>
P 528			19.5	1.1	17.4	3.4	1.0	101	18.4
<b>P 529</b>			<b>19.5</b>	<b>1.1</b>	<b>15.4</b>	<b>3.0</b>	<b>0.4</b>	<b>103</b>	<b>18.1</b>
P 639			17.5	-0.8	14.9	2.6	0.4	97	16.3
<b>P 645</b>			<b>18.7</b>	<b>0.3</b>	<b>12.8</b>	<b>2.4</b>	<b>0.2</b>	<b>99</b>	<b>17.1</b>
P 673			17.6	-0.7	15.3	2.7	0.2	105	16.5
<b>P 675</b>			<b>18.8</b>	<b>0.4</b>	<b>13.8</b>	<b>2.6</b>	<b>0.4</b>	<b>119</b>	<b>17.3</b>
P 702			17.0	-1.4	18.2	3.1	0.6	117	16.2
<b>P 718</b>			<b>19.9</b>	<b>1.5</b>	<b>16.1</b>	<b>3.3</b>	<b>1.2</b>	<b>111</b>	<b>18.7</b>

P 722	17.0	-1.4	19.5	3.3	0.6	98	16.3
<b>P 733</b>	<b>19.3</b>	<b>1.0</b>	<b>15.5</b>	<b>3.0</b>	<b>0.6</b>	<b>93</b>	<b>18.0</b>
P 756	20.8	2.4	16.4	3.4	0.8	98	19.5
<b>P 758</b>	<b>18.1</b>	<b>-0.2</b>	<b>16.6</b>	<b>3.0</b>	<b>0.8</b>	<b>103</b>	<b>17.1</b>
P 778	19.0	0.7	15.8	3.0	0.2	89	17.8
<b>P 801</b>	<b>18.6</b>	<b>0.3</b>	<b>17.2</b>	<b>3.2</b>	<b>0.6</b>	<b>99</b>	<b>17.6</b>
P 843	17.3	-1.0	13.9	2.4	0.0	103	16.0
<b>P 886</b>	<b>19.5</b>	<b>1.1</b>	<b>16.0</b>	<b>3.1</b>	<b>0.6</b>	<b>105</b>	<b>18.2</b>
P 893	17.5	-0.9	14.9	2.6	0.4	108	16.2
<b>P 895</b>	<b>18.6</b>	<b>0.3</b>	<b>16.1</b>	<b>3.0</b>	<b>0.6</b>	<b>99</b>	<b>17.5</b>